

Average Stress, ksi, for 0.00001% Per Hour Minimum Creep Rate - Extrapolated

Alloy	Temperature, °F									
	900	1000	1100	1200	1300	1400	1500	1600	1700	1800
446	13	4.5	2	0.9	0.33	0.12	-	-	-	-
304L	-	7.8	5.1	3.25	2.1	1.34	0.88	-	-	-
304, 304H	-	17.9	11.1	7.2	4.5	2.9	1.8	-	-	-
316L	-	22.5	12	6.4	3.5	1.85	1	-	-	-
321	-	-	9.2	3.9	1.7	0.74	0.32	-	-	-
321H	-	-	12.4	7	4	2.25	1.28	-	-	-
347, 347H	-	30.5	16.2	8.7	4.7	2.5	1.3	-	-	-
RA 253 MA [®]	-	-	12	8.2	5.7	3.8	2.25	1.75	1.15	0.55
RA330 [®]	-	14.5	7.4	5.8	3.9	2.6	1.9	1.5	0.52	0.29
RA333 [®]	-	-	-	6.8	5.4	4.6	2.9	1.9	1.1	0.56
601	-	-	-	-	5.2	2.9	1.9	1.4	-	0.48